

RP-350

Polypropylene Random Copolymer


RP-350 is an injection molding copolymer certified prime resin designed for high speed injection of thin-walled applications requiring good impact resistance and very good clarity. **RP-350** exhibits very good dimensional stability and processability, rapid mold filling, high flow rate, fast cycle time, low warpage, and a good balance of mechanical properties. **RP-350** complies with FDA regulation 21CFR 177.1520 (a)(3)(i) / (c)3.1+3.2, and most international regulations concerning the use of Polypropylene in contact with food.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
PHYSICAL			
Melt Flow Rate (230°C, 2.16kg)	D1238	g/10 min	35
Density	D1505	g/cm ³	0.900
Rockwell Hardness (R-Scale)	D785		96
MECHANICAL			
Flexural Modulus ¹ (1% Secant)	D790	psi	180k
Tensile Strength @ Yield ²	D638	psi	4100
Notched Izod Impact (73°F)	D256	ft-lb/in	1.0
Tensile Elongation @ Yield ²	D638	%	11
HDT Under Load (66 psi Unannealed, Inj.)	D648	°F	185
Vicat Softening Temperature	D1525	°F	280

Typical Value of Properties not to be construed as specifications

1 - @ 0.051 in/min

2 - @ 2 in/min.



Genesis Polymers

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.