

# RP-350C

## Polypropylene Random Copolymer


**RP-350C** is a clarified injection molding certified prime copolymer designed for thin-walled applications requiring good impact resistance and outstanding clarity. **RP-350C** exhibits high flow rate, very good dimensional stability and processability, fast cycle time, high speed mold filling, low blooming, and good balance of mechanical properties. **RP-350C** complies with FDA regulation 21CFR 177.1520 (a)(3)(i) / (c)3.1+3.2, and most international regulations concerning the use of Polypropylene in contact with food.

PROPERTIES	ASTM	UNIT	NOMINAL VALUES
<b>PHYSICAL</b>			
Melt Flow Rate (230°C, 2.16kg)	D1238	g/10 min	35
Density	D1505	g/cm <sup>3</sup>	0.900
Rockwell Hardness (R-Scale)	D785		93
<b>MECHANICAL</b>			
Flexural Modulus <sup>1</sup> (1% Secant)	D790	psi	148k
Tensile Strength @ Yield <sup>2</sup>	D638	psi	4050
Notched Izod Impact (73°F)	D256	ft-lb/in	1.2
Tensile Elongation @ Yield <sup>2</sup>	D638	%	9.0
HDT Under Load (66 psi Unannealed, Inj.)	D648	°F	180
Vicat Softening Temperature	D1525	°F	273

Typical Value of Properties not to be construed as specifications

1 - @ 0.051 in/min

2 - @ 2 in/min.



# Genesis Polymers

The technical information, suggested uses and applications presented are made without charge and are believed to be reliable; however, the Ravago Group\* disclaims responsibility for reliance and results of use of this information. THE RAVAGO GROUP DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED, CONCERNING THE PRODUCT(S) DESCRIBED HEREINABOVE, INCLUDING ANY WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. The Ravago Group expressly disclaims any statements or suggestions as being inducement. All users should rely upon their own knowledge and testing in determining product suitability.